

## **Technical Data Sheet**

# PTAcross1207/1426

Cross-linkable Polyethylene

## **Product Description**

PTAcross 1207 is a silane grafted MDPE compound, curable by exposure to moist conditions, circulation of hot water or being at ambient. And shows good extrusion properties at high output rates. The highly cross-linked materials produced by the two-component system show excellent impact strength, ESCR, creep and internal pressure resistance under ambient and elevated temperature conditions.

PTAcross 1207 is designed for the requirements in ASTM F1281 for hot and cold water pressure multilayer pipes in outer layer.

PTAcross 1207 is used with PTAcross 1426 (a catalyst masterbatch) in the ratio of 95:5.

| General           |  |                                     |                               |
|-------------------|--|-------------------------------------|-------------------------------|
| Features          | <ul> <li>High Purity</li> </ul>                    | Good surface quality                |                               |
| Uses              | <ul> <li>High temperature pressure pipe</li> </ul> | <ul> <li>Multilayer pipe</li> </ul> | <ul><li>Outer layer</li></ul> |
| Processing Method | <ul> <li>Extrusion</li> </ul>                      |                                     |                               |
| Additives         | <ul> <li>Anti-oxidant</li> </ul>                   |                                     |                               |
| Appearance        | • White  |                                     |                               |
| Form              | • Pellets  |                                     |                               |
| Packaging         | • 25 Kg sacks                                      |                                     |                               |

| Physical                               | Typical value | Unit     | i est ivietnoa |
|--|---------------|----------|----------------|
| Density                                | 0.945         | g/cm³    | ASTM D1505     |
| Melt Mass-Flow Rate (MFR) (190°C/5 kg) | 4.0±1.0       | g/10 min | ASTM 1238      |
| Mechanical                             | Typical Value | Unit     | Test Method    |
| Tensile Strength                       | 21±2          | MPa      | ASTM D638      |
| Elongation (Break)                     | >500          | %        | ASTM D638      |
| Gel content                            | 70            | %        | ASTM D2765     |
| Established                            |               |          |                |

### As a guide the following temperature profile is recommended:

| Zone 1 | Zone 2 | Zone 3 | Zone 4 | Head | Die |
|--------|--------|--------|--------|------|-----|
| 140    | 160    | 180    | 190    | 210  | 220 |

#### Storage

This product should be stored in dry place away from sunlight

Web: <a href="www.pitaris.com">www.pitaris.com</a>Tele:+983132243765Email: <a href="mailto:lnfo@pitaris.com">lnfo@pitaris.com</a>Fax:+983132243765